

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES


Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



The **Delphion
Integrated
View**

Other Views:
INPADOC | Derwent...

Title: **JP5147997A2: PRODUCTION OF ROOF
ACCESSARY**

Country: **JP Japan**
Kind: **A**

Inventor(s): **MAEKAWA TOYOHICO**

Applicant/Assignee: **KUBOTA CORP**
News, Profiles, Stocks and More about this
company

Issued/Filed **June 15, 1993 / Nov. 26, 1991**

Dates:
Application **JP1991000337538**

Number:
IPC Class: **C04B 28/02; B28B 3/00; C04B 28/02;**


Priority **Nov. 26, 1991 JP1991000337538**

Number(s):
Abstract:



Purpose: To make mold release easy and to eliminate use of a template and a pallet in a method for producing a roof accessory by press molding.

Constitution: 8-12wt.% clay is added to a cement blend constituted of 40-50wt.% cement, 40-50wt.% silica sand and 2-5wt.% reinforcing fiber. Furthermore, 0.6-1.0wt.% methyl cellulose for cement and, by outer percentage, 2-4wt.% pigment are added to 100wt.% blended material. Furthermore, by outer percentage, 28-30wt.% water is added and the mixture is kneaded. This kneaded



V
lr
1


material is introduced into a mold, molded and dehydrated by pressing. A molded body is released from the mold and cured in an autoclave. Shape retention is remarkably enhanced by addition of clay.

COPYRIGHT: (C)1993,JPO&Japio

Family: Show known family members

Other Abstract Info: CHEMABS 119(14)145308S CAN119(14)145308S DERABS C93-224140 DERC93-224140

Foreign References: No patents reference this one



Nominate
this for
the
Gallery...



05

(19)

(11) Publication number:

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **03337538**(51) Intl. Cl.: **C04B 28/02 B28B**(22) Application date: **26.11.91**

(30) Priority:		
(43) Date of application	15.06.93	(71) Applicant: KUBOTA COI
publication:		(72) Inventor: MAEKAWA TO
(84) Designated contracting states:		(74) Representative:

(54) PRODUCTION OF ROOF ACCESSARY

(57) Abstract:

PURPOSE: To make mold release easy and to eliminate use of a template and a pallet in a method for producing a roof accessory by press molding.

CONSTITUTION: 8-12wt.% clay is added to a cement blend constituted of 40-50wt.% cement, 40-50wt.% silica sand and 2-5wt.% reinforcing fiber. Furthermore, 0.6-1.0wt.%

methyl cellulose for cement and, by outer percentage, 2-4wt.% pigment are added to 100wt.% blended material. Furthermore, by outer percentage, 28-30wt.% water is added and the mixture is kneaded. This kneaded material is introduced into a mold, molded and dehydrated by pressing. A molded body is released from the mold and cured in an autoclave. Shape retention is remarkably enhanced by addition of clay.

COPYRIGHT: (C)
1993,JPO&Japio